Test Report No. 7191065605-MEC13/C-MHA dated 22 Aug 2013

Note: This report is issued subject to the Testing and Certification Regulations of the TÜV SÜD Group and the General Terms and Conditions of Business of TÜV SÜD PSB Pte Ltd. In addition, this report is governed by the terms set out within this report.



Choose certainty.

Add value.

SUBJECT:

Non-combustibility test on "Everest Boards" submitted by Everest Industries Ltd on 23 Jul 2013.

TESTED FOR:

Everest Industries Ltd A-32, Genesis Mohan Co-Operative Industrial Estate Mathura Road New Delhi – 110044 India

PERIOD OF TEST:

25 Jul 2013 and 26 Jul 2013

PURPOSE OF TEST:

To determine whether the material is non-combustible when it is exposed to the conditions of the test specified in British Standard 476: Part 4: 1970 "Fire Test on Building Materials and Structures - Non-combustibility Test for Materials".

The test was conducted at TÜV SÜD PSB's fire test laboratory located at No. 10 Tuas Avenue 10, Singapore 639134.





Laboratory: TÜV SÜD PSB Pte. Ltd. No.1 Science Park Drive Singapore 118221



Phone: +65-6885 1333

Fax: +65-6776 8670

www.tuv-sud-psb.sg

Co. Reg: 199002667R

E-mail: testing@tuv-sud-psb.sg



LA-2007-0380-A LA-2007-0381-F LA-2007-0382-B LA-2007-0383-G LA-2007-0384-G LA-2007-0385-E LA-2007-0386-C

LA-2010-0464-D

The results reported herein have been performed in accordance with the laboratory's terms of accreditation under the Singapore Accreditation Council - Singapore Laboratory Accreditation Scheme. Tests/Calibrations marked 'Not SAC-SINGLAS Accredited' in this Report are not included in the SAC-SINGLAS Accreditation Schedule for our laboratory.

Regional Head Office: TÜV SÜD Asia Pacific Pte. Ltd. 3 Science Park Drive, #04-01/05 The Franklin, Singapore 118223

Test Report No. 7191065605-MEC13/C-MHA dated 22 Aug 2013



DESCRIPTION OF SAMPLES:

Twenty pieces of specimen, said to be "Everest Boards" (18mm thick x 1450kg/m³ – 1600kg/m³) comprising of Fibre Cement, each of nominal size of 40mm x 40mm were submitted. The nominal thickness and bulk density of the specimen were found to be approximately 18.3mm and 1605kg/m³ respectively. Six blocks of specimen, each of nominal test size of 40mm x 40mm x 50mm thickness were prepared.

TEST PROCEDURE:

Specimens were exposed to the specified heating conditions (750 \pm 10°C) in a furnace conforming to Clause 6 and illustrated in Figure 1, 2 and 3 of the Standard. The furnace was heated and its temperature stabilized at 750 \pm 10°C for more than 10 minutes. One specimen was then inserted in the furnace, the whole operation was performed in less than 5 seconds. The temperature of the specimens and the furnace were measured by two separate Chromel/Alumel thermocouples continuously for 20 minutes on the chart of a recorder. The flaming time of the specimen was determined by a stop watch. The procedure was repeated twice for two other specimens, one at each time.

RESULTS:

| | Specimen 1 | Specimen 2 | Specimen 3 | Requirements |
|-----------------------------------|-------------|-------------|-------------|--------------|
| Description | | | | |
| Time of continuous flaming (sec.) | 0 | 0 | 0 | <10 |
| Temperature rise of furnace (°C) | 40 | 43 | 45 | <50 |
| Temperature rise of sample (°C) | 0 | 0 | 0 | <50 |
| Classification | Non- | Non- | Non- | - |
| | combustible | combustible | combustible | |

CONCLUSION:

A non-combustibility test for materials in accordance with British Standard 476 Part 4: 1970 has been performed on the material as described in this report and the classification of the sample is non-combustible.

REMARKS:

The testing was witnessed by Mr. Sharad Mali from Everest Industries Ltd.

Ung Klan Huat Higher Associate Engineer Chan Ling Toa
Product Manager
(Fire Property)
Mechanical Centre

Test Report No. 7191065605-MEC13/C-MHA dated 22 Aug 2013



Please note that this Report is issued under the following terms:

- 1. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
- 2. The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
- 3. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
- 4. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
- 5. Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, No.1 Science Park Drive Singapore 118221.

