



Entwicklungs- und Prüflabor
Holztechnologie GmbH
Zellescher Weg 24 · D-01217 Dresden
www.eph-dresden.de



Deutsche
Akkreditierungsstelle
D-PL-11054-01-00
D-ZE-11054-01-00
accredited by Deutsche Akkreditierungsstelle GmbH (DAkkS)

T E S T C E R T I F I C A T E

CT-13-09-23-02

Product: HOMAPAL - Laminate with artificial leather surface

Manufacturer: Homapal GmbH
Bahnhofstraße 30/32
D-37412 Herzberg

Order: Determination of the Formaldehyde release of HOMAPAL - Laminate with artificial leather surface according to the test chamber method DIN EN 717-1

Test method: Chamber test method DIN EN 717-1
Chemical analysis formaldehyde: Acetyl-Acetone-Method


Test report: Test report 2513388 dated September 23rd, 2013

Test result: The formaldehyde release of the tested HOMAPAL - Laminate with artificial leather surface is 0.01 ppm (168 h).
The tested HOMAPAL - Laminate with artificial leather surface meets the limited value of 0.1 ppm of the ChemVerbotsV § 1 (3).

Dresden, September 23rd, 2013




Head of laboratory


Engineer in charge