

Test Report No. 7191058019-MEC13/B1-MHA
dated 17 Jun 2013



PSB Singapore

Choose certainty.
Add value.

Note: This report is issued subject to the Testing and Certification Regulations of the TÜV SÜD Group and the General Terms and Conditions of Business of TÜV SÜD PSB Pte Ltd. In addition, this report is governed by the terms set out within this report.

SUBJECT:

Large scale surface spread of flame test on "Everest Heavy Duty Board" submitted by Everest Industries Ltd on 17 Apr 2013.

TESTED FOR:

Everest Industries Ltd
A-32, Genesis
Mohan Co-Operative Industrial Estate
Mathura Road
New Delhi – 110044
India

DATE OF TEST:

24 Apr 2013

PURPOSE OF TEST:

To determine the tendency of the surface of a material or a combination of materials to support the spread of flame across its surface and to classify the surface according to the test given in British Standard 476 : Part 7 : 1997.

The test was conducted at TÜV SÜD PSB's fire test laboratory located at No. 10 Tuas Avenue 10, Singapore 639134.

This test report supersedes test report dated on 02 May 2013



Laboratory:
TÜV SÜD PSB Pte. Ltd.
No.1 Science Park Drive
Singapore 118221

		LA-2007-0380-A LA-2007-0381-F LA-2007-0382-B LA-2007-0383-G LA-2007-0384-G LA-2007-0385-E LA-2007-0386-C LA-2010-0464-D	The results reported herein have been performed in accordance with the laboratory's terms of accreditation under the Singapore Accreditation Council - Singapore Laboratory Accreditation Scheme. Tests/Calibrations marked "Not SAC-SINGLAS Accredited" in this Report are not included in the SAC-SINGLAS Accreditation Schedule for our laboratory.
--	--	--	--

Phone : +65-6885 1333
Fax : +65-6776 8670
E-mail: testing@tuv-sud-psb.sg
www.tuv-sud-psb.sg
Co. Reg : 199002667R

Regional Head Office:
TÜV SÜD Asia Pacific Pte. Ltd.
3 Science Park Drive, #04-01/05
The Franklin, Singapore 118223
TUV®

DESCRIPTION OF SPECIMENS:

Nine pieces of specimen, said to be “Everest Heavy Duty Board” (15mm thick x $1350\text{kg/m}^3 - 1450\text{kg/m}^3$) comprising of Fibre Cement, each of nominal test size of 885mm x 270mm were submitted. The bulk density of the sample was found to be approximately 1596kg/m^3 .

TEST PROCEDURE:

Prior to test, the specimens were prepared and conditioned in accordance with paragraphs 5.3 to 5.6 of the standard and secured to a specimen holder as described in paragraph 6.3.

Six specimens, backed with calcium silicate board, were tested with the Front face exposed to the specified thermal radiation from the apparatus described in paragraph 6.1 of the standard. The intensity of the radiated heat incident on the specimen varies with distance from the hotter end, so that when the specified calibration panel is mounted in the place to be occupied by the specimen, the irradiance of the radiometer is as given in Table 1. The test was terminated when the flame front reached the 825mm reference line, or after 10 minutes has elapsed, whichever is the shorter.

Table 1 : Irradiance Along Horizontal Reference Line on the Calibration Board

Distance along reference line from inside edge of specimen holder mm	Irradiance kW/m^2		
	specified	min.	max.
75	32.5	32.0	33.0
225	21.0	20.5	21.5
375	14.5	14.0	15.0
525	10.0	9.5	10.5
675	7.0	6.5	7.5
825	5.0	4.5	5.5



This test report supersedes test report dated on 02 May 2013



RESULTS OF TEST:

Specimen No.	1	2	3	4	5	6
Spread of flame at first 1½ minutes (mm)	0	0	0	0	0	0
Distance (mm)	Time of spread of flame to indicated distance (minutes • seconds)					
Start of flaming	nil	nil	nil	nil	nil	nil
75	-	-	-	-	-	-
165	-	-	-	-	-	-
190						
215						
240						
265						
290						
375						
455						
500						
525						
600						
675						
710						
750						
785						
825						
865						
Time of maximum spread of flame (minutes • seconds)	-	-	-	-	-	-
Distance of maximum spread of flame (mm)	0	0	0	0	0	0
Comments	None					

This test report supersedes test report dated on 02 May 2013

Classification of Surface Spread of Flame

Classification	Spread of flame at 1.5 min.		Final spread of flame	
	Limit (mm)	Limit for one specimen in sample (mm)	Limit (mm)	Limit for one specimen in sample (mm)
Class 1	165	165 + 25	165	165 + 25
Class 2	215	215 + 25	455	455 + 45
Class 3	265	265 + 25	710	710 + 75
Class 4	Exceeding the limits for class 3			

CONCLUSION:

In accordance with the class definitions specified in the Standard, the test results show that the sample tested has a Class One Surface Spread of Flame.

REMARKS:

1. The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.
2. To change the name from "Everest" Heavy Duty Fibre Cement Board to "Everest Heavy Duty Board".



Ong Kian Huat
Higher Associate Engineer



Chan Lung Toa
Product Manager
(Fire Property)
Mechanical Centre

This test report supersedes test report dated on 02 May 2013

Test Report No. 7191058019-MEC13/B1-MHA
dated 17 Jun 2013




PSB Singapore

Please note that this Report is issued under the following terms :

1. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
2. The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
3. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
4. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
5. Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, No.1 Science Park Drive Singapore 118221.

July 2011



This test report supersedes test report dated on 02 May 2013